

Micronized Wax Type List

Model No	Particle size D50(μm)	Density	Melting Point	Counterpart Products	Application
iSuo SP-3620	6.0-8.0	0.95-0.96	115-120	L-1588SF; CC-3620; S-S-393	Ink (Offset, gravure)
iSuo SP-29	4.0-6.0	0.95-0.96	116-121	MP-615VF; C-MX9510; B-AF-29-s; D-MX-9815, CC-3620	Ink (Offset, gravure, Flexo, UV), steel & can coating
iSuo SP-C5	3.5-5.0	0.95-0.96	116-121	HW-C5	Ink (Offset, gravure)
iSuo SP-C3	3.5-5.0	0.95-0.96	120-125	HW-AC-C3	Ink (Offset, gravure)
iSuo SP-30	5.0-7.0	0.95-0.96	116-121	B-AF-30-s	Ink (Offset, gravure), powder coating
iSuo SP-5	4.0-6.0	0.95-0.97	115-121	D-MX-9815; S-394N1; M-MPP-615VF; CC-3620	Ink (Offset, gravure), wood coating, steel & can coating
iSuo SP-6	5.0-7.0	0.95-0.97	115-121	D-MX-9820, LP-1401, B-990-991, C-3620, L-1588	Ink (Offset, gravure), wood coating, powder coating, steel & can coating
iSuo SP-9	8.0-9.0	0.95-0.96	115-121	L-1588LF;	Ink (Offset, gravure), powder coating
iSuo SP-D6	5.0-6.0	0.95-0.98	116-118	D-MX-9820; HW-D-6	Ink (Offset, gravure , Flexo)
iSuo SP-31	9.0-10.0	0.95-0.98	116-118	HW-D-9; S-379H; B-AF-31,32-s	Ink (Offset, gravure , Flexo), textile ink
iSuo SP-H1	pellets	0.95-0.96	120	S-H1	Powder coating
iSuo SP990	7.0-8.5	0.96-0.97	130.00	B-990-991, C-3620, L-1588	Ink
iSuo WP-32W	5.5-7.5	0.94-0.95	110-115	C-3715; S-5223NL; B-AF-31,32-w; M-2200EF	Water based ink, wood coating, leather coating
iSuo WP-205	5.5-7.5	0.94-0.95	110-115	C-3715	Water based ink, wood coating
iSuo WP-3175	6.0-8.0	0.98	137	C-3715	Water based ink, wood coating, leather coating
iSuo SP-12	10.0-13.0	0.98	132-138	HW-A-12	Ink
iSuo SP-18	15.0-20.0	0.98	132-138	HW-A-18	Ink
iSuo PA-960K	4.0-5.0	0.95-0.97	145	L-1601, 1602; B-960; CC-3910, B-993, B-994	Powder coating
iSuo PA-993k	4.0-5.0	0.95-0.97	145	B-993, B-994	Powder coating
iSuo PA-961K	5.5-7.5	0.99-1.01	140-143	B-961, B-962, D-9220	Powder coating
iSuo PA-962K	5.5-7.5	0.99-1.01	140-145	B-961, B-962	Powder coating
iSuo 2003S	4.5-5.5	0.97-0.98	139-144	L-1400SF; S-2003;	wood coating, Powder coating
iSuo 154L	8.0-9.0	0.99	135-145	LL-1544F	wood coating, powder coating, steel & can coating
iSuo PTFE-92	1.5-2.0			S-SST-4MG	ink, powder coating, steel & can coating
iSuo PTFE-81K	2.0-3.0	2.1-2.2	323-327	S-TF-9205, B-981, L-1792	ink, powder coating, steel & can coating
iSuo PTFE-91K	39.0-41.0	2.1-2.2	323-327	B-913, B-915, B-965, L-1890	ink, powder coating

Micronized Wax Type List

Model No	Particle size D50(μm)	Density	Melting Point	Counterpart Products	Application
iSuo M-778	5.0-6.0	0.95-0.97	120-327	L-TF1778, L-TF1780; CC-9610F; B-996, CC-3920F	ink, powder coating, wood coating, steel & can coating
iSuo M-725	4.0-5.0	0.98-1.00	120-327	L-TF1725, LL-TF1789	ink, powder coating, steel & can coating
iSuo M-510D	4.0-5.0	0.98-1.00	120-327	D-9510D	ink, powder coating, wood coating, steel & can coating
iSuo M-997K	≤5	0.95-0.97	115-327	L-TF1778, B-996-998, L-1778	ink, powder coating, steel & can coating
iSuo PP-H5	5.0-6.0	0.89-0.90	150-160	HW-P-5, A-WN-1135, B-970, L-TP1362D	powder coating, floor painting
iSuo M-70	6.0-7.0	0.89-0.90	150-160	B-970, L-TP1362D	ink, powder coating
iSuo M-1362	8.5-9.5	0.96	140-150	B-970, L-TP1362D	ink, powder coating
iSuo M-56	4.0-6.0	0.99	120-250		ink, coating and leather
iSuo CN-6	5.0-7.0	0.99	80-86		ink, coating and leather
iSuo CN-4	3.0-5.0	1.18	120-320		can coating, bake coating, anish
iSuo PF-362	5.00	0.95-0.96	100.00	1588	steel & can coating, gravure ink
iSuo PF-394N	5.00	0.95-0.96	102.00	S-394N1, D-MX-9815; S-394N1; M-MPP-615VF; SS-105	steel & can coating, gravure ink
iSuo PF-15	4.00	0.94-0.95	102.00	S-SP-30, SS-105	Ink (Offset, gravure), powder coating
iSuo 9610F	7.5-9.5	0.95-0.97	128.00	CC-3920F, LL-TF1725, CC-9610F, LL-TF1789	Powder coating
iSuo 150F	3.0-4.0	0.95-0.96	120-320	MP-150	ink, steel & can coating
iSuo PA-50	Beads	-	116-119	SM-50	Ink (Offset, gravure)
iSuo S-395	5.5-7.5	0.95-0.97	115-120	D-T-3915	Ink (Offset, gravure), powder coating, can coating, wood coating
iSuo PE520	Beads	-	112.50	S-H1, C-L-PE 520	powder coating , plastic, hot-melt adhesive, textile, ink
iSuo SP-219	8.0-10.0	0.93-0.94	112-113		powder coating , plastic, textile, ink
iSuo SP-218	7.0-9.0	0.93-0.94	112-113	M-J-U2200	powder coating , plastic, textile, ink
iSuo SP-216	5.0-7.0	0.93-0.94	112-113	B-990-991, C-3620, L-1588, M-J-U2200	powder coating , plastic, textile, ink
iSuo SP-215	4.0-6.0	0.93-0.94	112-113	B-990-991, C-3620, L-1588	powder coating , plastic, textile, ink
iSuo SP-951		0.95-0.97	125.00	MX-9815 & 9510	Ink, wood coating
iSuo SP-951A	6.0-8.0	0.95-0.97	125.00	MX-9815 & 9510	Ink, wood coating